

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : F16L 9/12, 11/12		A1	(11) International Publication Number: WO 93/21466
			(43) International Publication Date: 28 October 1993 (28.10.93)
(21) International Application Number: PCT/US93/03479		(74) Agent: GLASSMEYER, Denise, M.; Basile and Hanlon, 1650 West Big Beaver Road, Suite 210, Troy, MI 48084 (US).	
(22) International Filing Date: 13 April 1993 (13.04.93)			
(30) Priority data:		(81) Designated States: European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
07/868,754	14 April 1992 (14.04.92)	US	
07/897,302	11 June 1992 (11.06.92)	US	
07/897,376	11 June 1992 (11.06.92)	US	
(71) Applicant: ITT INDUSTRIES, INC. [US/US]; 1105 North Market Street, Suite 1217, Wilmington, DE 19801 (US).		Published <i>With international search report.</i>	
(72) Inventors: NOONE, David, L. ; 29200 Candlewood, South- field, MI 48076 (US). MITCHELL, Frank, L. ; 662 N. Main Street, Apt. 103, Rochester, MI 48307 (US). WE- NIG, Peter ; Karl-Reinke-Strasse 1, D-3538 Marsberg - Bredelar (DE).			

(54) Title: MULTI-LAYER FUEL AND VAPOR TUBE

(57) Abstract

A layered tubing (10) for use in a motor vehicle composed of a thick outer tubing (12) having an inner and an outer face, the outer tubing (12) made of an extrudable thermoplastic such as a polyamide like Nylon 12; a thin intermediate bonding layer (16) bonded to the inner face of the thick outer layer (12), the bonding layer (16) composed of an extrudable melt-processible thermoplastic capable of sufficiently permanent laminar adhesion to the polyamide outer tubing (12); and an inner hydrocarbon barrier layer (14) bonded to the intermediate bonding layer (16), the inner layer (14) composed of an extrudable, melt processible thermoplastic capable of sufficiently permanent laminar adhesion with the intermediate bonding layer (16), the thermoplastic containing as a major constituent a fluoroplastic such as polychlorotrifluoroethylene, ethylene tetrafluorethylene, polyvinylidene fluoride, polyvinyl fluoride, and the like.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SU	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

MULTI-LAYER FUEL AND VAPOR TUBEI. Field of the Invention:

5 The present invention relates to a hose for use in a motor vehicle. More particularly, the present invention relates to a multi-layer hose which can be employed as a fuel line or vapor recovery line in a motor vehicle.

II. Background of the Invention:

10 Single layer fuel lines and vapor return lines of synthetic materials such as polyamides have been proposed and employed in the past. Fuel lines employing such materials generally have lengths of at least several meters. It is important that the line, once installed,
15 not materially change during the length of operation, either by shrinkage or elongation or as a result of the stresses to which the line may be subject during use.

 It is also becoming increasingly important that the lines employed be essentially impervious to
20 hydrocarbon emissions due to permeation through the tubing. It is anticipated that future Federal and state regulations will fix the limit for permissible hydrocarbon emissions due to permeation through such lines. Regulations which will be enacted in states such
25 as California will fix the total passive hydrocarbon emission for a vehicle at 2 g/m² per 24 hour period as calculated by evaporative emission testing methods such as those outlined in Title 13 of the California Code of Regulations, section 1976, proposed amendment of
30 September 26, 1991. To achieve the desired total vehicle emission levels, a hydrocarbon permeation level for the lines equal to or below 0.5 g/m² per 24 hour period would be required.

35 Finally, it is also imperative that the fuel line employed be impervious to interaction with corrosive materials present in the fuel such as oxidative agents and surfactants as well as additives such as ethanol and methanol.

Various types of tubing have been proposed to address these concerns. In general, the most successful of these have been co-extruded multi-layer tubing which employ a relatively thick outer layer composed of a material resistant to the exterior environment. The innermost layer is thinner and is composed of a material which is chosen for its ability to block diffusion of materials such as aliphatic hydrocarbons, alcohols and other materials present in fuel blends, to the outer layer. The materials of choice for the inner layer are polyamides such as Nylon 6, Nylon 6.6, Nylon 11, and Nylon 12.

Alcohol and aromatics in the fluid conveyed through the tube diffuse at different rates through the tubing wall from the aliphatic components. The resulting change in the composition of the liquid in the tubing can change the solubility thresholds of the material so as, for example, to be able to crystalize monomers and oligomers of materials such as Nylon 11 and Nylon 12 into the liquid. The presence of copper ions, which can be picked up from the fuel pump, accelerates this crystallization. The crystallized precipitate can block filters and fuel injectors and collect to limit travel of the fuel-pump or carburetor float as well as build up on critical control surfaces of the fuel pump.

In U.S. Patent Number 5,076,329 to Brunnhofer, a five-layer fuel line is proposed which is composed of a thick outer layer formed of Nylon 11 or Nylon 12, a thick intermediate layer of Nylon 6, and a thin intermediate bonding layer between and bonded to the intermediate and outer layers formed of a polyethylene or a polypropylene. On the interior of the tube is an inner layer of Nylon 6 with a thin intermediate solvent-blocking layer formed of an ethylene-vinyl alcohol copolymer transposed between. The use of Nylon 6 in the inner fluid contacting surface is designed to eliminate

at least a portion of the monomer and oligomer dissolution which occurs with Nylon 11 or Nylon 12.

5 In U.S. Patent Number 5,038,833 to Brunnhofer, a three-layer fuel line is proposed in which a tube is formed having a co-extruded outer wall of Nylon 11 or Nylon 12, an intermediate alcohol barrier wall formed from an ethylene-vinyl alcohol copolymer, and an inner water-blocking wall formed from a polyamide such as Nylon 11 or Nylon 12. In DE 40 06 870, a fuel line is proposed 10 in which an intermediate solvent barrier layer is formed of unmodified Nylon 6.6 either separately or in combination with blends of polyamide elastomers. The internal layer is also composed of polyamides; preferably modified or unmodified Nylon 6 while the outer layer is 15 composed of either Nylon 6 or Nylon 12.

Another tubing designed to be resistant to alcoholic media is disclosed in UK Application Number 2 204 376 A in which a tube is produced which has an thick outer layer composed of polyamides such as Nylon 6 or 6.6 20 and/or Nylon 11 or 12 which are co-extruded with an alcohol-resistant polyolefin, a co-polymer of propylene and maleic acid.

Heretofore it has been extremely difficult to obtain satisfactory lamination characteristics between 25 dissimilar polymer layers. Thus all of the multi-layer tubing proposed previously has employed polyamide-based materials in most or all of the multiple layers. While many more effective solvent-resistant chemicals exist, their use in this area is limited due to limited 30 elongation properties, strength and compatibility with Nylon 11 and 12. Additionally, the previous disclosures fail to address or appreciate the phenomenon of electrostatic discharge.

Electrostatic discharge can be defined as the 35 release of electric charge built up or derived from the passage of charged particles through a medium or conduit composed of essentially non-conductive materials. The

electrostatic charge is repeatedly replenished with the passage of additional volumes of fuel through the conduit. Discharge repeatedly occurs in the same localized area gradually eroding the area and leading to eventual rupture leading to the danger of fire and explosion of the flammable contents of the tubing.

Thus it would be desirable to provide a tubing material which could be employed in motor vehicles which would be durable and prevent or reduce permeation of organic materials therethrough. It would also be desirable to provide a tubing material which would be essentially nonreactive with components of the liquid being conveyed therein. Finally, it would be desirable to provide a tubing material which would be capable of preventing the build-up of electrostatic discharge therein or would be capable of safely dissipating any electrostatic charge induced therein.

SUMMARY OF THE INVENTION

The present invention is a multi-layer tube which can be used on motor vehicles for applications such as in a fuel line or a vapor return or recovery line. The tube of the present invention is composed of:

a thick flexible outer tubing having an inner and an outer face, the outer tubing consisting essentially of an extrudable melt processible thermoplastic having an elongation value of at least 150% and an ability to withstand impacts of at least 2 ft/lbs at temperatures below about -20°C;

a thin intermediate bonding layer bonded to the inner face of the thick outer layer, the bonding layer consisting essentially of an extrudable melt processible thermoplastic capable of sufficiently permanent laminar adhesion to the outer tubing; and

an inner hydrocarbon barrier layer bonded to the intermediate bonding layer, the inner layer consisting of an extrudable melt processible thermoplastic capable of sufficiently permanent laminar

adhesion with the intermediate bonding layer, the thermoplastic containing as a major constituent a fluoroplastic selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, polyvinylidene fluoride, polyvinyl fluoride, and mixtures thereof.

The inner hydrocarbon layer may be capable of dissipating electrostatic energy, the electrostatic dissipation capacity being in a range between about 10^{-4} to 10^{-9} ohm/cm².

DESCRIPTION OF THE DRAWING

The objects, features and advantages of the present invention will become more readily apparent from the following description, reference being made to the following drawing in which the Figure is a sectional view through a piece of tubing of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention is a multi-layer fuel line and vapor tube which contains at least one bonding layer and at least an outer and an inner tubing layer. The tubing of the present invention is, preferably, fabricated by co-extruding given thermoplastic materials in a conventional co-extrusion process. The tubing may either be co-extruded to a suitable length or may be co-extruded in continuous length and cut to fit the given application subsequently. The tubing of the present invention may have an outer diameter up to 50 mm. However, in applications such as fuel lines and vapor recovery systems, outer diameter of up to 2.5 inches are preferred.

The material may have any suitable wall thickness desired. However, in automotive systems such as those described herein, wall thicknesses between 0.5 mm and 2 mm are generally employed with wall thicknesses of approximately 0.8 mm to approximately 1.5 mm being preferred; and wall thicknesses between about 0.8 mm and about 1.25 mm being most preferred. While it is within

the scope of this invention to prepare a tubing material having a plurality of overlaying layers of various thermoplastic materials, the tubing of the present invention generally has a maximum of five layers inclusive of the bonding layers. In the preferred embodiment, the tubing material has three or four.

The tubing 10 of the present invention is a material which is suitable for use in motor vehicles and comprises a relatively thick outer layer 12 which is non-reactive with the external environment and can withstand various shocks, vibrational fatigue, and changes in temperature as well as exposure to various corrosive or degradative compounds to which it would be exposed through the normal course of operation of the motor vehicle.

It is anticipated that both the outer tubing layer 12 as well as any interior layers bonded thereto would be suitable for use at an outer service temperature range between about -40°C and about 150°C , with a range of -20°C to 120°C being preferred. The various layers of tubing are integrally laminated to one another and resistant to delamination throughout the lifetime of the tubing. The tubing thus formed will have a tensile strength of no less than 25N/mm^2 and an elongation value of at least 150%. The tubing will have a burst strength at 23°C and 120°C of at least 20 bar. The multi-layer tubing of the present invention is sufficiently resistant to exposure to brake fluid, engine oil and peroxides such as those which may be found in gasoline.

In the first embodiment of the present invention, the multilayer tubing comprises an outer layer consisting essentially of a thermoplastic material selected from the group consisting of 12 carbon block polyamides, 11 carbon block polyamides, thermoplastic elastomers, and mixtures thereof; an inner layer consisting essentially of a thermoplastic material selected from the group consisting essentially of

polyvinylidene fluoride, polyvinyl fluoride, and mixtures thereof; and an intermediate bonding layer consisting essentially of an extrudable thermoplastic capable of sufficiently permanent laminar adhesion to the polyamide outer tubing selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, and mixtures thereof.

In the second embodiment of the present invention, the multilayer tubing comprises an outer layer consisting essentially of a thermoplastic material selected from the group consisting of 12 carbon block polyamides, 11 carbon block polyamides, thermoplastic elastomers, and mixtures thereof; an inner layer consisting essentially of a thermoplastic material selected from the group consisting essentially of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, and mixtures thereof; and an intermediate bonding layer consisting essentially of an extrudable thermoplastic capable of sufficiently permanent laminar adhesion to the polyamide outer tubing selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, blends of polyvinyl acetate and urethane, and mixtures thereof.

In the third embodiment of the present invention, the multilayer tubing comprises an outer layer consisting essentially of a thermoplastic 6-carbon block polyamide; an inner layer consisting essentially of a thermoplastic material selected from the group consisting essentially of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, and mixtures thereof; and an intermediate bonding layer consisting essentially of an extrudable thermoplastic capable of sufficiently permanent laminar adhesion to the polyamide outer tubing selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, blends of polyvinyl acetate and urethane, and mixtures thereof.

In general, the outer layer 12 may be composed of any melt-processible extrudable thermoplastic material which is resistant to ultra violet degradation, extreme changes in heat and exposure to environmental hazards such as zinc chloride, and degradation upon contact with engine oil and brake fluid. In the first and second embodiments of the present invention, the exterior layer is selected from the group consisting of 12 carbon block polyamides, 11 carbon block polyamides, thermoplastic elastomers, and mixtures thereof. Where thermoplastic elastomers are employed, it is anticipated that the elastomer will be a proprietary material commercially available under tradenames such as SANTOPRENE, VICHEM, KRATON, or SARLINK, or mixtures of these materials. The materials which compose the outer layer can be present in their unmodified state or can be modified with various plasticizers, flame retardants and the like in manners which would be known to one reasonably skilled in the art.

In the first and second embodiments, a polyamide such as Nylon 12 can be effectively employed. If modified, it is anticipated that the material will contain various plasticizers as are readily known in the art. The polyamide material employed, preferably, is an impact-modified material capable of withstanding impacts of 2 ft/lbs at temperatures below about -20°C.

In the third preferred embodiment, the outer layer is composed of a polyamide thermoplastic derived from the condensation polymerization of caprolactam. Such materials are commonly referred to as a 6-carbon block polyamide or Nylon 6. In this third embodiment, the 6-carbon block polyamide either inherently exhibits zinc chloride resistance or contains sufficient quantities of modifying agents to impart a level of zinc chloride resistance greater than or equal to that required by test method SAE J844; non-reactivity after 200 hour immersion in a 50% by weight zinc chloride solution. The Nylon 6

which composes the outer layer of the tubing of this embodiment can also be modified with various plasticizers, flame retardants and the like in manners which would be known to one reasonably skilled in the art. In this embodiment, the 6-carbon block polyamide material is preferably a multi-component system comprised of a Nylon-6 copolymer blended with other Nylons and olefinic compounds. The zinc chloride resistant Nylon-6 of choice will have a melt temperature between about 220°C and 240°C. Examples of thermoplastic materials suitable for use in the tubing of the present invention are proprietary materials which can be obtained commercially under the tradenames M-7551 from NYCOA Corporation and ALLIED 1779 from Allied Chemical.

The 6-carbon black polyamide may, optionally, include other modifying agents such as various plasticizing agents generally present in amounts between about 1.0% and about 13% by total weight of the thermoplastic composition as are readily known in the art. The polyamide material employed, preferably, is an impact-modified material capable of withstanding impacts of at least 2 ft. lbs. at temperatures below about -20°C.

The outer layer 16 has a wall thickness sufficient to provide suitable strength and endurance to the multi-layer tubing of the present invention. In applications involving automotive vehicles, the outer layer 12 comprises between about 50% and about 70% of the total wall thickness. In general, the outer layer has a wall thickness between about 0.6 mm and about 0.9 mm; with a preferred wall thickness between about 0.7 mm and about 0.8 mm, and a most preferred wall thickness between about 0.7 and about 0.75mm. As indicated previously, the material can be extruded by conventional co-extrusion methods to any continuous length desired.

The inner layer 14 is integrally bonded to the inner surface of the thick outer polyamide layer 12. In the present invention, the inner layer 14 is a chemically

dissimilar, permeation resistant, chemical resistant, fuel resistant thermoplastic material which is melt processible in normal ranges of extrusion, i.e. about 175°C to about 250°C. By the term "chemically

5 dissimilar" it is meant that the inner layer 14 consists essentially of a non-polyamide material which is capable of adhesion to a bonding layer interposed between the thick outer layer and the inner layer in a manner which will be described subsequently.

10 In each of the preferred embodiments, the thermoplastic material which comprises the inner layer is a fluoroplastic material selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, polychlorotrifluoroethylene, ethylene
15 tetrafluoroethylene copolymers, and mixtures thereof. In the first embodiment, it is preferred that the fluoroplastic material be selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, and mixtures thereof. In the second and third
20 embodiments, it is preferred that the fluoroplastic material be selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, and mixtures thereof.

In the first embodiment, the thermoplastic
25 material which comprises the inner layer is, preferably, a polyvinylidene fluoroplastic derived from the thermal dehalogenation of chlorodifluoroethane commercially available under the tradenames "FLORAFLON" and "KYNAR" from Atochem Inc. elf Aquitaine Group of Philadelphia,
30 Pennsylvania.

In the second embodiment, the preferred
material is an ethylene tetrafluoroethylene copolymer
having a melt temperature between about 270°C and 560°C
and a specific gravity of 1.7. The ethylene
35 tetrafluoroethylene copolymer employed herein is derived from the copolymerization of ethylene with tetrafluoroethylene. The preferred polymeric material

has an ethylene-derived content between about 40% and about 70% and a tetrafluoroethylene content between about 30% and about 60% by total polymer weight with minor amounts of proprietary materials being optionally present. Suitable materials are commercially available under the tradenames "TEFZEL 210", "TEFZEL 200", and "TEFZEL 280" from I.G. duPont de Nemours, Inc. of Wilmington, Delaware.

In the third embodiment, the thermoplastic material which comprises the inner layer is a fluoroplastic material selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers and mixtures thereof. The material employed will, preferably, have a melt temperature between about 270°C and 560°C and a specific gravity of 1.7. Suitable polychlorotrifluoroethylene fluoroplastic materials may be derived from the pyrolysis of chlorodifluoromethane. Suitable ethylene tetrafluoroethylene copolymers are proprietary materials. It is believed that such materials broadly have ethylene-derived contents between about 40% and about 70%; tetrafluoroethylene contents between about 30% and about 60% by total polymer weight; and minor amounts of proprietary materials. Suitable materials are commercially available under the tradenames "TEFZEL 210", "TEFZEL 200", and "TEFZEL 280" from I.G. duPont de Nemours, Inc. of Wilmington, Delaware.

The thermoplastic material employed in the inner layer 14 is capable of serving as a hydrocarbon barrier to prevent significant permeation of the aromatic and aliphatic components of gasoline through to the polyamide outer layer 12 of the tubing 10 and thus, out to the surrounding environment.

Preferably, the inner layer 14 may also exhibit conductive characteristics rendering it capable of dissipation of electrostatic charge in the range of 10^{-4} to 10^{-9} ohm/cm². The fluoroplastic material employed in

optionally include sufficient amounts of conductive media to effect electrostatic dissipation in the range of 10^{-4} to 10^{-9} ohm/cm². As with the inner layer, the intermediate bonding layer may be inherently electrostatically dissipative or may be rendered so by the inclusion of certain conductive material such as those selected from the group consisting of elemental carbon, stainless steel, copper, silver, gold, nickel, silicon and mixtures thereof.

It is preferred that the inner layer 14 and the bonding layer 16 be maintained at the minimum thickness necessary to prevent permeation of the fuel through the tubing material. It is preferred that the amount of hydrocarbon permeation through the tubing 10 be no greater than 0.5 gm/m² in a 24 hour interval. The thickness of the inner layer can be varied to accomplish this end.

In the preferred embodiment, the inner layer has the minimum wall thickness sufficient to achieve the permeation resistance desired. In general, the inner layer is thinner than the outer layer with the thickness of the outer layer being between about 50% and about 60% of the total wall thickness of the multi-layer tubing. Preferably, the inner wall thickness is between about 0.01 mm and about 0.2 mm with a thickness of about 0.05 mm and about 0.2 mm being preferred and a thickness between about 0.05 mm and about 0.17 mm being most preferred.

The intermediate bonding layer 16 is of sufficient thickness to permit an essentially homogeneous bond between the inner and outer layers. In general, the intermediate bonding layer can be thinner than the other two layers and can constitute between about 10% and about 20% of the total wall thickness of the multi-layer tube. In the preferred embodiment, the thickness of the intermediate bonding layer is between about 0.01 mm and about 0.2 mm with a thickness between about 0.05 mm and

about 0.2 mm being preferred; and a thickness between about 0.05 mm and about 0.15 mm being most preferred.

5 The total wall thickness of the tubing of the present invention is generally between about 0.5 mm and about 2.0 mm with a wall thickness between about 0.8 and about 1.25 mm being preferred.

The tubing of the present invention may also, optionally include an outer jacket (not shown) which surrounds the outer layer. The fourth outer jacket may
10 be either co-extruded with the other layers during the extrusion process or may be put on in a subsequent process such as cross-extrusion. The outer jacket may be made of any material chosen for its structural or insulating characteristics and may be of any suitable
15 wall thickness. In the preferred embodiment, the outer jacket may be made of a thermoplastic material selected from the group consisting of zinc-chloride resistant Nylon 6, Nylon 11, Nylon 12, polypropylene, and thermoplastic elastomers such as SANTOPRENE, KRATON,
20 VICHEM and SARLINK. If desired, these materials may be modified to include flame retardants, plasticizers and the like.

What is claimed is:

1. A layered tubing for use in a motor vehicle, the tubing comprising:

a thick flexible outer tubing having an inner and an outer face, the outer tubing consisting essentially of an extrudable melt-processible thermoplastic having an elongation value of at least 150% and an ability to withstand impacts of at least 2 ft/lbs at temperatures below about -20°C;

a thin intermediate bonding layer bonded to the inner face of the thick outer layer, the bonding layer consisting essentially of an extrudable melt processible thermoplastic capable of sufficiently permanent laminar adhesion to the inner face of the outer tubing; and

an inner hydrocarbon barrier layer bonded to the intermediate bonding layer, the inner layer consisting of an extrudable, melt-processible thermoplastic capable of sufficiently permanent laminar adhesion with the intermediate bonding layer, the melt-processible thermoplastic consisting essentially of a fluoroplastic selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, polyvinyl fluoride, polyvinylidene fluoride and mixtures thereof.

2. The tubing of claim 1 wherein the inner hydrocarbon barrier layer has is capable of dissipating electrostatic energy, the electrostatic dissipation capacity being in a range between about 10^{-4} to 10^{-9} ohm/cm².

3. The tubing of claim 1 wherein the inner hydrocarbon layer contains quantities of a conductive material sufficient to provide electrostatic dissipation capability in a range between about 10^{-4} to 10^{-9} ohm/cm².

4. The tubing of claim 3 wherein the conductive material is selected from the group consisting of elemental carbon, copper, silver, gold, nickel, silicon, and mixtures thereof.

5 5. The tubing of claim 4 wherein the conductive material is present in an amount less than about 5% by volume of the polymeric material.

6. The tubing of claim 4 wherein the conductive material is interstitially integrated into the melt-processible fluoroplastic material.

7. The tubing of claim 4 wherein the conductive material is elemental carbon and is copolymerized with the extrudable fluoroplastic material.

8. The tubing of claim 1 wherein the extrudable thermoplastic of the thick outer tubing is a polyamide selected from the group consisting of Nylon 11, Nylon 12, zinc chloride resistant Nylon 6, Santoprene, Kraton, Vichem, Sarlink and mixtures thereof.

9. The tubing of claim 1 wherein the thermoplastic material employed in the intermediate bonding layer exhibits at least some resistance to interaction with short-chain hydrocarbon molecules present in material conveyed through the tubing.

10. The tubing of claim 9 wherein the thermoplastic material employed in the intermediate bonding layer includes as a major constituent an extrudable, melt processible thermoplastic selected from the group consisting of polyvinylidene fluoride, polyvinyl fluoride, blends of polyvinyl acetate and urethane, and mixtures thereof.

11. The tubing of claim 1 further comprising an exterior jacket overlying the thick outer tubing, the exterior jacket composed of a material consisting essentially of a thermoplastic rubber selected from the group consisting of Nylon 11, Nylon 12, zinc chloride resistant Nylon 6, Santoprene, Kraton, Vichem, Sarlink and mixtures thereof.

12. A layered tubing for use in a motor vehicle, the tubing comprising:

an outer tubing having an inner and an outer face, the outer tubing consisting essentially of an extrudable polyamide having an elongation value of at least 150% and an ability to withstand impacts of at least 2 ft/lbs at temperatures below about -20°C;

an intermediate bonding layer having a thickness between about 0.05 mm and about 0.2 mm bonded to the inner face of the thick outer layer, the bonding layer consisting essentially of an extrudable thermoplastic capable of sufficiently permanent laminar adhesion to the polyamide outer tubing; and

an inner hydrocarbon barrier layer bonded to the intermediate bonding layer having a thickness between about 0.05 mm and about 0.2 mm, the inner layer consisting essentially of an extrudable, melt process fluoroplastic capable of sufficiently permanent laminar adhesion with the intermediate bonding layer selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, polyvinylidene fluoride, polyvinyl fluoride and mixtures thereof.

13. The tubing of claim 12 wherein the extrudable thermoplastic of the thick outer tubing is a polyamide selected from the group consisting of Nylon 11, Nylon 12, zinc chloride resistant Nylon 6 and mixtures thereof.

14. The tubing of claim 12 wherein the inner hydrocarbon barrier layer is selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers and mixtures thereof.

5 15. The tubing of claim 14 wherein the extrudable thermoplastic of the thick outer tubing is derived by the condensation polymerization of carprolactam.

10 16. The tubing of claim 14 wherein the extrudable thermoplastic of the thick outer tubing is a polyamide selected from the group consisting of Nylon 11, Nylon 12 and mixtures thereof.

15 17. The tubing of claim 13 further comprising an exterior jacket overlying the thick outer tubing, the exterior jacket composed of a material consisting essentially of a thermoplastic rubber selected from the group consisting of Nylon 11, Nylon 12, zinc chloride resistant Nylon 6, Santoprene, Kraton, Vichem, Sarlink, polypropylene and mixtures thereof.

20 18. The tubing of claim 12 wherein the thermoplastic material of the inner hydrocarbon barrier layer is capable of dissipating electrostatic energy, the electrostatic dissipation capacity being in a range between about 10^{-4} to 10^{-9} ohm/cm².

25 19. The tubing of claim 12 wherein the thermoplastic material of the inner hydrocarbon barrier layer contains quantities of a conductive material
sufficient to provide electrostatic dissipation capacity
in a range between about 10^{-4} to 10^{-9} ohm/cm².

30 20. The tubing of claim 16 wherein the conductive material is selected from the group consisting

of elemental carbon, copper, silver, gold, nickel, silicon, and mixtures thereof and is present in an amount less than about 5% by volume of the extrudable thermoplastic material.

5 21. The tubing of claim 16 wherein the conductive material is interstitially integrated into the melt processible fluoroplastic material.

 22. The tubing of claim 16 wherein the conductive material is elemental carbon and is
10 copolymerized with the extrudable fluoroplastic material.

 23. The tubing of claim 12 wherein the extrudable thermoplastic of the intermediate bonding layer is a thermoplastic selected from the group consisting of polyvinylidene fluoride, polyvinyl
15 fluoride, blends of polyvinyl acetate and urethane, and mixtures thereof.

 24. A layered tubing for use in a motor vehicle, the tubing comprising:

 a thick flexible outer tubing having an inner
20 and an outer face, the outer tubing consisting essentially of an extrudable melt-processible thermoplastic having an elongation value of at least 150% and an ability to withstand impacts of at least 2 ft/lbs at temperatures below about -20°C;

25 a thin intermediate bonding layer bonded to the inner face of the thick outer layer, the bonding layer consisting essentially of an extrudable melt processible thermoplastic capable of sufficiently permanent laminar
adhesion to the inner face of the outer tubing, the
30 bonding layer selected from the group consisting of polyvinyl fluoride, polyvinylidene fluoride, blends of polyvinyl acetate and mixtures thereof; and

an inner hydrocarbon barrier layer bonded to the intermediate bonding layer, the inner layer consisting of an extrudable, melt-processible thermoplastic capable of sufficiently permanent laminar
5 adhesion with the intermediate bonding layer, the melt-processible thermoplastic consisting essentially of a fluoroplastic selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, polyvinyl fluoride, polyvinylidene fluoride
10 and mixtures thereof.

25. The tubing of claim 24 wherein the inner hydrocarbon layer contains quantities of a conductive material sufficient to provide electrostatic dissipation capability in a range between about 10^{-4} to 10^{-9} ohm/cm²
15 said conductive material selected from the group consisting of elemental carbon, copper, gold, silver, nickel, silicon, and mixtures thereof.

26. The tubing of claim 25 wherein the conductive material is present in an amount less than
20 about 5% by volume of the polymeric material.

27. The tubing of claim 26 wherein the extrudable thermoplastic of the thick outer tubing is a polyamide selected from the group consisting of Nylon 11, Nylon 12, zinc chloride resistant Nylon 6, Santoprene,
25 Kraton, Vichem, Sarlink and mixtures thereof.

28. The tubing of claim 27 wherein the thermoplastic material employed in the intermediate bonding layer exhibits at least some resistance to
interaction with short-chain hydrocarbon molecules
30 present in material conveyed through the tubing.

29. The tubing of claim 28 wherein the intermediate bonding layer is selected from the group

consisting of polyvinylidene fluoride, polyvinyl fluoride and mixtures thereof and has a thickness between about 0.05 mm and about 0.2 mm;

5 the inner hydrocarbon barrier layer has a thickness between about 0.05 mm and about 2.0 mm and is selected from the group consisting of polyvinyl fluoride, polyvinylidene fluoride, and mixtures thereof; and


10 the outer tubing is selected from the group consisting of Nylon 11, Nylon 12, Santoprene, Kraton, Vichem, Sarlink and mixtures thereof.

30. The tubing of claim 28 wherein:

the outer tubing is selected from the group consisting of Nylon 11, Nylon 12, Santoprene, Kraton, Vichem, Sarlink and mixtures thereof;

15 the intermediate bonding layer has a thickness between about 0.05 mm and about 0.2 mm and is selected from the group consisting of polyvinyl fluoride, polyvinylidene fluoride and mixtures thereof; and

20 the inner hydrocarbon barrier layer bonded to the intermediate bonding layer has a thickness between about 0.05 mm and about 0.2 mm, the inner layer consisting essentially of a fluoroplastic selected from the group consisting of polychlorotrifluoroethylene, ethylene tetrafluoroethylene copolymers, and mixtures
25 thereof.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/03479

I. CLASSIFICATION F SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 F16L9/12; F16L11/12		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	F16L	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
P, X	DATABASE WPIL Section Ch, Week 9239, Derwent Publications Ltd., London, GB; Class A04, AN 92-320278 & JP,A,4 224 939 (TOKAI RUBBER IND LTD.) 14 August 1992 see abstract ---	1, 24
A	DATABASE WPIL Section Ch, Week 9132, Derwent Publications Ltd., London, GB; Class A04, AN 91-232783 & JP,A,3 149 486 (SANYO ELECTRIC KK. & TOYOK KK.) 26 June 1991 see abstract --- -/--	1, 8, 11-13, 16, 17, 24, 27, 29, 30
¹⁰ Special categories of cited documents : ^{"A"} document defining the general state of the art which is not considered to be of particular relevance ^{"E"} earlier document but published on or after the international filing date ^{"L"} document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) ^{"O"} document referring to an oral disclosure, use, exhibition or other means ^{"P"} document published prior to the international filing date but later than the priority date claimed ^{"T"} later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention ^{"X"} document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step ^{"Y"} document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. ^{"&"} document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
09 JUNE 1993		29. 06. 93
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		BUDTZ-OLSEN A.

Form PCT/ISA/210 (extra sheet) (January 1985)